



(12) **United States Patent**
Langford

(10) **Patent No.:** **US 9,388,079 B2**
(45) **Date of Patent:** **Jul. 12, 2016**

(54) **LOW DUST WALL REPAIR COMPOUND**

(56) **References Cited**

(75) Inventor: **Nathaniel P. Langford**, Somerset, WI (US)

(73) Assignee: **3M Innovative Properties Company**, St. Paul, MN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 688 days.

(21) Appl. No.: **13/466,489**

(22) Filed: **May 8, 2012**

(65) **Prior Publication Data**

US 2012/0216944 A1 Aug. 30, 2012

Related U.S. Application Data

(60) Division of application No. 12/124,206, filed on May 21, 2008, which is a continuation of application No. 11/357,872, filed on Feb. 17, 2006, now Pat. No. 7,407,996, which is a continuation of application No. 11/029,759, filed on Jan. 5, 2005, now Pat. No. 7,052,544, which is a division of application No. 10/788,053, filed on Feb. 26, 2004, now Pat. No. 6,863,723, which is a division of application No. 09/821,392, filed on Mar. 29, 2001, now Pat. No. 6,733,581, which is a continuation-in-part of application No. 09/208,782, filed on Dec. 10, 1998, now Pat. No. 6,358,309.

(51) **Int. Cl.**

C04B 26/06 (2006.01)
C04B 26/02 (2006.01)
C04B 26/04 (2006.01)
C08K 5/01 (2006.01)
C04B 40/00 (2006.01)
C08K 3/00 (2006.01)
C09K 3/22 (2006.01)
C04B 103/00 (2006.01)
C04B 111/00 (2006.01)
C04B 111/72 (2006.01)

(52) **U.S. Cl.**

CPC **C04B 26/06** (2013.01); **C04B 26/02** (2013.01); **C04B 26/04** (2013.01); **C04B 40/0039** (2013.01); **C08K 3/0033** (2013.01); **C08K 5/01** (2013.01); **C09K 3/22** (2013.01); **C04B 2103/0075** (2013.01); **C04B 2111/00672** (2013.01); **C04B 2111/00681** (2013.01); **C04B 2111/723** (2013.01)

(58) **Field of Classification Search**

CPC C04B 26/02; C04B 26/04; C04B 2103/0075; C04B 2111/00672; C04B 2111/00681; C04B 2111/723

USPC 106/250; 427/403, 407.1, 416, 417
See application file for complete search history.

U.S. PATENT DOCUMENTS

2,117,833	A	5/1938	Wellner
3,183,107	A	5/1965	Alford
3,984,269	A	10/1976	Schneller
4,038,443	A	7/1977	Jacoby
4,073,968	A	2/1978	Miyamoto
4,136,050	A	1/1979	Brehm
4,171,276	A	10/1979	Brehm
4,238,239	A	12/1980	Brown
4,269,721	A	5/1981	Mueller
4,286,995	A	9/1981	Smith
4,294,622	A	10/1981	Brown
4,311,656	A	1/1982	Spriggs
4,316,811	A	2/1982	Burns
4,336,071	A	6/1982	Schnorrer
4,369,121	A	1/1983	Callahan
4,370,167	A	1/1983	Mudd
4,380,459	A	4/1983	Netting
4,391,647	A	7/1983	Deer
4,391,648	A	7/1983	Ferrill
4,400,220	A	8/1983	Cole, Jr.
4,417,992	A	11/1983	Bhattacharyya
4,425,252	A	1/1984	Cargle
4,428,984	A	1/1984	Shimizu
4,451,605	A	5/1984	Theodore
4,454,267	A *	6/1984	Williams 524/43
4,469,612	A	9/1984	Fenton
4,487,615	A	12/1984	Taylor
4,549,966	A	10/1985	Beall

(Continued)

FOREIGN PATENT DOCUMENTS

CA	763000	7/1967
CA	1117989	2/1982
CA	2163191 A	5/1997
DE	199 54 829 A1	5/2001
EP	0 008 030 A1	2/1980
EP	0 352 585	1/1990
EP	0 445 653	9/1991
EP	0 530 084 B1	3/1996
FR	2554120 A1	5/1985
GB	892 015	3/1962

(Continued)

OTHER PUBLICATIONS

Definitions of "cementitious" and "cement", Webster's II New Riverside University Dictionary, 242 (1984).

Primary Examiner — Kelechi Egwim

(74) Attorney, Agent, or Firm — Sandra K. Nowak

(57)

ABSTRACT

A wall repair compound useful for filling and repairing cracks, holes, and other imperfections in a wall surface includes a conventional filler material, a conventional binder material, and a dust reducing additive which reduces the quantity of airborne dust particles generated when sanding the hardened joint compound. Airborne dust reducing additives include oils, surfactants, solvents, waxes, and other petroleum derivatives. The additive can be added to conventional ready-mixed joint compounds and to setting type joint compounds. A method of reducing the quantity of airborne dust generated when sanding a fully hardened joint compound includes mixing a sufficient quantity of the dust reducing additive with the joint compound prior to when the joint compound has been applied to the wall.

12 Claims, 1 Drawing Sheet